




PCT/GB 2004 / 0 0 5 2 6 2



INVESTOR IN PEOPLE

The Patent Office
Concept House
Cardiff Road
Newport



BEST AVAILABLE COPY

I, the undersigned, being an officer duly authorised in accordance with Section 74(1) and (4) of the Deregulation & Contracting Out Act 1994, to sign and issue certificates on behalf of the Comptroller-General, hereby certify that annexed hereto is a true copy of the documents as originally filed in connection with the patent application identified therein.

In accordance with the Patents (Companies Re-registration) Rules 1982, if a company named in this certificate and any accompanying documents has re-registered under the Companies Act 1980 with the same name as that with which it was registered immediately before re-registration save for the substitution as, or inclusion as, the last part of the name of the words "public limited company" or their equivalents in Welsh, references to the name of the company in this certificate and any accompanying documents shall be treated as references to the name with which it is so re-registered.

In accordance with the rules, the words "public limited company" may be replaced by p.l.c., plc, P.L.C. or PLC.

Re-registration under the Companies Act does not constitute a new legal entity but merely subjects the company to certain additional company law rules.

Signed

Stephen Hordley

Dated

10 January 2005

**PRIORITY
DOCUMENT**


SUBMITTED OR TRANSMITTED IN
COMPLIANCE WITH RULE 17.1(a) OR (b)



1/77
22DEC03 E861025-1 D02903
P01/7700 0.00-0329531.8 ACCOUNT CHA

Request for grant of a patent

(See the notes on the back of this form. You can also get an explanatory leaflet from the Patent Office to help you fill in this form)



The Patent Office

Cardiff Road
Newport
South Wales
NP10 8QQ

1. Your reference 11376P4 GB/CMB

2. Patent application number 19 DEC 2003 0329531.8
(The Patent Office will fill this part in)

3. Full name, address and postcode of the or of each applicant (underline all surnames)
Reckitt Benckiser N.V.
Kantoorgebouw De Appelaer
De Fruittuinen 2-12
2132 NZ Hoofddorp
Netherlands
07921075005

Patents ADP number (if you know it)

If the applicant is a corporate body, give the country/state of its incorporation Netherlands

4. Title of the invention Injection Moulded Containers

5. Name of your agent (if you have one) Craig M Bowers
Group Patents Department
Reckitt Benckiser plc
Dansom Lane
Hull
HU8 7DS
United Kingdom

"Address for service" in the United Kingdom to which all correspondence should be sent (including the postcode)

Patents ADP number (if you know it) 07799521001

6. Priority: Complete this section if you are declaring priority from one or more earlier patent applications, filed in the last 12 months.	Country	Priority application number (if you know it)	Date of filing (day / month / year)
---	---------	--	-------------------------------------

7. Divisionals, etc: Complete this section only if this application is a divisional application or resulted from an entitlement dispute (see note f)	Number of earlier UK application	Date of filing (day / month / year)
--	----------------------------------	-------------------------------------

8. Is a Patents Form 7/77 (Statement of inventorship and of right to grant of a patent) required in support of this request? Yes

Answer YES if:

- a) any applicant named in part 3 is not an inventor, or
- b) there is an inventor who is not named as an applicant, or
- c) any named applicant is a corporate body.

Otherwise answer NO (See note d)

9. Accompanying documents: A patent application must include a description of the invention. Not counting duplicates, please enter the number of pages of each item accompanying this form:

Continuation sheets of this form

Description	47
Claim(s)	5
Abstract	1
Drawing(s)	3 + 3 <i>RM</i>

10. If you are also filing any of the following, state how many against each item.

Priority documents

Translations of priority documents

Statement of inventorship and right to grant of a patent (Patents Form 7/77)

Request for a preliminary examination and search (Patents Form 9/77) One

Request for a substantive examination (Patents Form 10/77) One

Any other documents (please specify) FS1

11. I/We request the grant of a patent on the basis of this application.

Signature(s)

Craig M Bowers
Craig M Bowers

Date 17 December 2003

12. Name, daytime telephone number and e-mail address, if any, of person to contact in the United Kingdom

Craig M Bowers

01482 583730 Craig.Bowers@ReckittBenckiser.com

Warning

After an application for a patent has been filed, the Comptroller of the Patent Office will consider whether publication or communication of the invention should be prohibited or restricted under Section 22 of the Patents Act 1977. You will be informed if it is necessary to prohibit or restrict your invention in this way. Furthermore, if you live in the United Kingdom, Section 23 of the Patents Act 1977 stops you from applying for a patent abroad without first getting written permission from the Patent Office unless an application has been filed at least 6 weeks beforehand in the United Kingdom for a patent for the same invention and either no direction prohibiting publication or communication has been given, or any such direction has been revoked.

Notes

- If you need help to fill in this form or you have any questions, please contact the Patent Office on 08459 500505.
- Write your answers in capital letters using black ink or you may type them.
- If there is not enough space for all the relevant details on any part of this form, please continue on a separate sheet of paper and write "see continuation sheet" in the relevant part(s). Any continuation sheet should be attached to this form.
- If you have answered YES in part 8, a Patents Form 7/77 will need to be filed.
- Once you have filled in the form you must remember to sign and date it.
- Part 7 should only be completed when a divisional application is being made under section 15(4), or when an application is being made under section 8(3), 12(6) or 37(4) following an entitlement dispute. By completing part 7 you are requesting that this application takes the same filing date as an earlier UK application. If you want the new application to have the same priority date(s) as the earlier UK application, you should also complete part 6 with the priority details.

INJECTION MOULDED CONTAINERS

The present invention relates to a process for preparing a container by injection moulding a composition comprising a water soluble polymer, such as poly(vinyl alcohol) (PVOH).

Clothes washing compositions may be delivered to a clothes washing machine by a delivery tray from which the composition is fed into the washing drum, or they may be placed directly into the washing drum. The washing compositions may be in powder, liquid or block form. Liquid compositions have the disadvantage that they may be spilt. The same applies to powder compositions. Powder compositions have the additional disadvantage that they may produce dust which can be inhaled. These problems are overcome or lessened when blocks of washing composition are used. These are normally individually wrapped. On unwrapping a block, for use, it is still possible that some dust may be produced. Additionally it is an inconvenience for the consumer to have to unwrap the block. Furthermore it is almost impossible for the user to avoid some contact between the block and his or her skin, so leading to a requirement for the user to wash their hands after starting the washing machine. In fact, all of the methods described involve a risk of contact between the composition and the skin, and it is desirable in all cases for the user to wash their hands after starting the washing machine. In this context it should be borne in mind that many compositions contain enzymes to assist the cleaning action. Even though the user may tolerate enzyme residues which may be left in

clothes after washing, they may still not tolerate contact between the concentrated washing composition containing the enzymes, and the skin.

5 Similar considerations apply in relation to other areas including fabric care, surface care and dishwashing. Thus, in relation in particular to dishwashing compositions, there are also problems of spillage, dust generation, skin contact and
10 inconvenience.

It is known to package chemical compositions which may be of a hazardous or irritant nature in water-soluble or water-dispersible materials such as films. The
15 package can simply be added to water in order to dissolve or disperse the contents of the package into the water.

For example, WO 89/12587 discloses a package which comprises an envelope of a water-soluble or water-
20 dispersible material which comprises a flexible wall and a water-soluble or water-dispersible heat seal. The package may contain an organic liquid comprising, for example, a pesticide, fungicide, insecticide or herbicide.

25 CA-A-1,112,534 discloses a packet made of a water-soluble material in film form enclosing within it a paste-form, automatic dishwasher-compatible detergent composition. The water-soluble material may be, for
30 example, poly(vinyl alcohol), polyethylene oxide or methyl cellulose.

It is also known to form water-soluble containers by thermoforming a water-soluble material. For example, WO 92/17382 discloses a package containing an agrochemical such as a pesticide comprising a first sheet of non-planar water-soluble or water-dispersible material and a second sheet of water-soluble or water-dispersible material superposed on the first sheet and sealed to it by a continuous closed water-soluble or water-dispersible seal along a continuous region of the superposed sheets.

The above methods of packaging have, however, a number of disadvantages.

The first disadvantage is that they do not have a particularly attractive appearance. In fields such as containers used in the domestic environment, an attractive appearance for an article is extremely desirable. Liquids contained in envelopes of water-soluble film can have a limp, unattractive appearance.

The second disadvantage is that it is difficult to form two or more separate compartments in the packaging so that two incompatible components are both enclosed but separated from each other. Although an arrangement has been described to separate incompatible materials in flexible pouches in WO 93/08095, the method proposed is complex and is not currently achievable in large-scale manufacturing. It cannot, therefore, be used for producing large numbers of containers.

The third disadvantage is that there is only limited control of the release profile of the compositions held

in the containers. For example, when a composition is held between two planar water-soluble films or in a thermoformed package, the composition is simply released at the time when the films dissolve or disperse in water. While it may be possible to control to a certain extent the timing of the start of release of the contents, there can be no control over the rate of release of the contents since the entire film dissolves or disperses at about the same time. Furthermore it can be difficult to provide an extended time before the contents of the package are released. An additional problem also arises with thermoformed packages. If the thermoforming is not carefully controlled there may be inadvertent thinning of the film material at the points where the material is drawn down into the mould when it is thermoformed. This could release the contents of the package early. Additionally, in all of the above packages, it is not possible to release different compositions at different times or at different rates since, as discussed above, it is not possible to incorporate more than one composition in each water-soluble container.

The fourth disadvantage is that the containers cannot be produced at a particularly fast rate. When the containers are produced by heat-sealing planar films or by thermoforming, the containers have to be immediately filled and sealed. All of these procedures have to be carried out in succession. This means that it is not possible to obtain a quick throughput for mass-market goods such as household products. For example, standard thermoforming machines can only produce around 400 to 800 containers per minute.

The present invention seeks to provide water-soluble containers which overcome some or all of the above disadvantages.

5

The present invention provides a process for the manufacture of a single or multi-compartment, rigid, water-soluble container, containing a detergent composition, wherein the container is at least partially
10 formed of injection moulded water soluble polymer; the process comprising the steps of forming the container, filling with the detergent composition and sealing.

Most preferably the container is allowed to contact
15 / brought into contact with a plasticiser after sealing. Preferably the plasticiser is gaseous or in vapour form.

Generally the plasticiser is water. Thus the present invention provides a process for the manufacture
20 of a single or multi-compartment, rigid, water-soluble container, containing a detergent composition, wherein the container is at least partially formed of injection moulded water soluble polymer; the process comprising the steps of forming the container, keeping the container
25 under substantially anhydrous conditions, filling with the detergent composition and sealing.

Surprisingly we have found that when the process of the present invention is used a rigid water soluble
30 container is produced. More specifically by keeping the injection moulded container in substantially anhydrous conditions after formation and before filling with the

detergent composition the rigidity of the container is preserved.

5 In this way we have found that in the preferred sealing process (see later) wherein a top sealing film is applied (usually in a pressure contact process) the container exhibits sufficient rigidity for effective joining/sealing of the film to occur.

10 Additionally we have also found that during the preferred filling operation (see later) the high rigidity of the container is especially beneficial.

15 The filling operation is usually performed using a dispensing apparatus. The dispensing apparatus commonly comprises a nozzle which directs the composition to be filled into the container. For multi-compartment containers, especially where each compartment is filled with a separate composition, it is vital that each
20 compartment be arranged relative to its appropriate dispensing means with high predictability to avoid incorrect dispense. This would otherwise lead to detrimental interaction of compartment compositions (if more than one composition is dispensed into one
25 compartment) or wastage of compartment compositions (if a composition is dispensed outside the container). The method in accordance with the invention allows this high level of predictability to be achieved. Therefore filling issues caused by incorrect dispense are
30 minimised.

The anhydrous retention conditions may be effected using common environmental controlled means. As an example, if the containers are to be stored before filling the storage conditions need to be controlled so
5 that the humidity level is low. This can be achieved by the use of de-humidifiers controlling the atmosphere of the area where the containers are stored. Alternatively a number of containers may be stored in a sealed enclosure (such as a water-tight bag/box, e.g. a
10 metal/plastic vessel) from which the bulk of the available moisture is withdrawn. The latter method is particularly suitable, where the containers need to be transported from the site of formation to the site of filling.

15

Most preferably the containers are kept under substantially anhydrous conditions until filling.

The containers produced in accordance with the
20 invention need not be kept under anhydrous conditions (once filled with the detergent composition and sealed). After time the containers will begin to absorb moisture either from the air or from the composition held within (if the composition is an aqueous liquid composition
25 containing free water). It is believed that the water plasticises the water-soluble polymer, which was dried during the injection moulding process. It is believed that water (from the air or from an aqueous composition held within the container) lowers the rigidity of the
30 container.

The reduction in rigidity has several benefits. Firstly, although high rigidity (as described above) is beneficial during the manufacturing (filling and/or sealing) process, consumers generally find overly rigid
5 containers unappealing. Following moisture uptake the container develops a desirable tactile quality highly regarded by consumers.

10 Additionally the reduction in rigidity (after processing) improves container stability in storage/transport. The low rigidity containers display a much greater ability to withstand impact during storage and transport. Thus undesirable rupture of containers is
15 vastly reduced.

The containers have the usual advantages associated with injection moulded containers. The containers have an attractive, uniform appearance which does not vary between different containers. Also, a wide variety of
20 different shapes and designs are available. Furthermore, rigid containers can easily have various elements incorporated which are considered to be pleasing to the eye.

25 Moreover, it is possible to control the release profile of the contents of the container. Since the container is rigid, it is possible to adapt the width of all of the walls of the container to control both the start of release of the composition as well as the rate
30 of release. For example, one or more walls may be made thin in order to have an early release of the composition. Alternatively all the walls may be thick in

order to ensure that there is a delayed release of the composition. The rate of release of the composition may also be controlled by ensuring that only part of the container has thin walls which are dissolved or dispersed
5 before the remainder of the container.

Preferably the water soluble polymer is PVOH or a derivative thereof.

10 Other water-soluble polymers may be used either as an alternative or in addition to PVOH. Preferred examples include poly(vinylpyrrolidone), poly(acrylic acid), poly(maleic acid), a cellulose derivative (such as an ether or hydroxypropyl methyl cellulose); and
15 poly(glycolide), poly(glycolic acid), poly(lactides), poly (lactic acid) or a copolymer thereof

It will be appreciated that the container may be made in part by any other water-soluble polymer.
20 Therefore, a further feature of the invention is a rigid, water-soluble container made of at least two injection moulded polymers, a "first" water-soluble polymer, preferably selected from poly(vinyl alcohol); a cellulose derivative (such as an ether or hydroxypropyl methyl
25 cellulose); and poly(glycolide), poly(glycolic acid), poly(lactides), poly (lactic acid) or a copolymer thereof; and a "second" water-soluble polymer which polymer when dissolved in water is active in detergency.

30 Thus in an alternative release control mechanism different walls or parts of walls of the container may be prepared from different water-soluble polymers which have

different dissolution characteristics. For example, a first compartment may be fully enclosed by a polymer which dissolves at a higher or lower temperature than the polymer enclosing a second compartment. Thus different
5 components can be released at different times. If the container holds a solid or gelled composition, it is not even necessary for the container to fully enclose the composition. A part may be left exposed, so that it immediately begins to dissolve when added to water.

10

It is possible for suitable additives such as plasticizers (other than water) and lubricants to be included. Plasticizers are generally used in an amount of up to 20wt%, for example from 8 to 20wt%, lubricants
15 are generally used in an amount of 0.5 to 5wt% and the polymer is generally therefore used in an amount of 75 to 84.5wt%, based on the total amount of the moulding composition.

20 Surprisingly we have found that if a plasticiser having a melting higher than room temperature is used then the rigidity of the containers formed is extremely high. This has the advantage that the containers maintain their shape after injection moulding. This in
25 particular surprising as water-soluble polymers, especially PVOH, have the non-desired characteristic to easily deform after the shaping process.

Thus preferred plasticisers comprise a carbohydrate.
30 Carbohydrates are usually represented by the generalised formula $C_x(H_2O)_y$. The term herein also includes materials which are similar in nature like gluconic acids or amino

sugars which cannot be fully represented by this formula. Other carbohydrate derivatives like sugar alcohols such as sorbitol, glucitol, mannitol, galactitol, dulcitol, xylitol, erythritol, isomaltutose and isomalt fall within
5 this term.

Most preferred carbohydrates include the more thermally stable carbohydrates such as sorbitol, glucitol, mannitol, galactitol, dulcitol, xylitol,
10 erythritol, isomaltutose and isomalt.

We have also found that when the containers are formed in the substantial absence of a plasticiser which is liquid at room temperature then the rigidity of the
15 containers after shaping is extremely high.

The container is generally cold water (20°C) soluble, but may be insoluble in cold water at 20°C and only become soluble in warm water or hot water having a
20 temperature of, for example, 30°C, 40°C, 50°C or even 60°C.

For certain applications or uses, containers soluble in aqueous environments at temperatures as low as 5°C are
25 also desirable.

In order to ensure that the polymer is capable of being injection moulded, it is usual to incorporate components such as plasticizers (as discussed above) and
30 mould release agents in an amount of up to, for example, 15wt% of the composition. Solids such as talc, stearic

acid, magnesium stearate, silicon dioxide, zinc stearate, and colloidal silica may be used as mould release agents.

Poly(vinylpyrrolidone) may be moulded at
5 temperatures of from 120-180°C, depending upon the formulation selected and the melt flow index required.

Poly(acrylic acid) may be moulded at temperatures of
from 180-220°C, for example, depending upon the
10 formulation selected and the melt flow index required.

Poly(maleic acid) may be moulded at temperatures of,
from 180-220°C for example, depending upon the
formulation selected and the melt flow index required.

15 PVOH may be moulded at temperatures of, for example, from 180-220°C, depending upon the formulation selected and the melt flow index required. The PVOH preferably used to form the container of the present invention may
20 be partially / fully alcoholised or hydrolysed. For example it may be from 40-99%, preferably 70-92%, more preferably about 88%, alcoholised or hydrolysed polyvinylacetate.

25 Preferably the container is a container enclosing a washing composition.

All of the polymer compositions may also include other components such as colouring agents and components
30 which modify their properties.

Injection moulding techniques are well known to the skilled person and are well described in the literature (see, for example a good summary is provided in "The Wiley Encyclopedia of Packaging Technology" Wiley Interscience 1986). Special techniques, described below, are preferred features of the invention for producing containers having more than one type of polymer.

Simultaneous injection moulding

10

1) two or more polymers are molten mixed and injected into a mould;

15

2) two or more polymers are injected into a mould through more than one gate, each gate allowing simultaneous injection of a single polymer or molten mix into the mould;

20

3) simultaneously injection moulding two or more compartments and then joining the compartments together.

Sequential injection moulding

25

1) multi-component injection moulding;

2) sandwich injection moulding;

30

3) sequentially injection moulding two or more;

4) compartments and then joining the compartments together.

Multi-component injection moulding covers two distinct processes

5 A) injection moulding a polymer or molten polymer mix into a mould, removing the solid polymer and inserting it into a second mould and injection moulding a second polymer or polymer mix into the second mould;

10

B) injection moulding a polymer or molten polymer mix into a part of a mould, injection moulding a second polymer or molten polymer mix into a further part of the mould.

15

Steps A) and B) may be repeated more than once and may be combined. It will be appreciated by the skilled person that the first injection moulded polymer must survive the pressure and temperature conditions of the second, or subsequent, injection moulding.

20

For step B) the first polymer or molten mix may be prevented from entering parts of the mould by any physical means, such as, gates, gravity, positive or negative pressure.

25

Sandwich injection moulding (or sometimes called skin-core injection moulding) comprises injection moulding a polymer or molten polymer mix into a mould until it is partially filled and then injecting a second polymer or molten polymer mix into the same mould through

30

the same gate to form the core. An additional step of sealing the core may be performed.

It will be appreciated that any combination of
5 simultaneous and sequential injection moulding may be used.

The closure part may itself be injection moulded or blow moulded. Preferably, however, it is a plastics film
10 secured over the receptacle part. The film may, for example, comprise PVOH or a cellulose ether such as HPMC or another water-soluble polymer.

Preferably for closing the container the receptacle
15 part and the closure are sealed together, for example by heat sealing. A suitable heat sealing temperature is 120 to 195°C, more preferably 140 to 150°C. The sealing pressure depends on the heat sealing machine used. A suitable sealing pressure is from 250 to 800 kPa (35 to
20 120 p.s.i.). Examples of sealing pressures are 400 to 800 kPa (60 to 120 p.s.i.), especially 276 to 552 kPa (40 to 80 p.s.i.), more especially 345 to 483 kPa (50 to 70 p.s.i.). Suitable sealing dwell times are at least 0.4 seconds, for example 0.4 to 2.5 seconds.

25

Other methods of sealing the receptacle part to the closure together may be used. These include infra-red, radio frequency, ultrasonic, laser, solvent, vibration, electromagnetic, hot gas, hot plate, insert bonding,
30 fraction sealing or spin welding. An adhesive such as water or an aqueous solution of PVOH may also be used. The adhesive can be applied to the sheets by spraying,

transfer coating, roller coating or otherwise coating, or the sheets can be passed through a mist of the adhesive.

5 The container walls have thicknesses such that the containers are rigid (as described above). For example, the outside walls and any inside walls which have been injection moulded independently have a thickness of greater than 100 μ m, for example greater than 150 μ m or greater than 200 μ m, 300 μ m, or 500 μ m, 750 μ m or 1mm.
10 Generally the walls are moulded so as to be as thin as possible to reduce container material consumption in the process and to make the dissolution time of the container as short as possible. Usually the wall thickness at more than 60% of the wall area is less than 800 μ m, more preferably less than 600 μ m and most preferably less than 15 400 μ m. Preferably, the closure part is of a thinner material than the receptacle part. If different compartments having different dissolution times are required, different wall thicknesses can be used. A
20 thickness difference of from 100 μ m to 500 μ m, preferably from 250 μ m to 350m, would give a suitable difference in release times.

25 Preferably, the closure part dissolves in water (at least to the extent of allowing the washing composition in the receptacle part to be dissolved by the water; and preferably completely) at 40°C in less than 5 minutes, preferably in less than 2 minutes.

30 The receptacle part and the closure part could be of the same thickness or different thicknesses. The closure

part may, for example, be of higher solubility than the receptacle part, in order to dissolve more quickly.

5 Preferably, the washing container is generally cuboid in its external shape, with the top wall being formed by the closure part, and with the side walls and base wall being formed by the receptacle part.

10 Preferably, a washing container of the invention is manufactured by forming an array of receptacle parts, each receptacle part being joined to adjacent receptacle parts, and being separable from them by a snap or tear action. The array is preferably one which has columns and rows of the receptacle parts. The receptacle parts
15 may be separated by frangible webs of the water-soluble polymer such as PVOH or a cellulose ether.

Alternatively, the receptacle parts may be manufactured with the aforementioned flanges, such that
20 they are separated from each other by a line of weakness. For example the material may be thinner, and so able to be broken or torn readily. The thinness may be a result of the moulding process or, preferably, of a later scoring step.

25

In the manufacturing method, the array, formed by injection moulding, is fed to a filling zone, and all the receptacle parts are charged with the washing composition. A sheet of a water-soluble polymer such as
30 PVOH or a cellulose ether may then be secured over the top of the array, to form the closure parts for all the receptacle parts of the array. The array may then be

split up into the individual washing capsules, prior to packaging, or it may be left as an array, for packaging, to be split by the user.

5 The container, capsule or receptacle part defines two or more compartments, which may contain different products useful in a washing process. In such a situation a dividing wall or walls of the compartments preferably terminate at the top of the container, i.e. in
10 the same plane as the top edges of the side walls, so that when the receptacle part is closed by the closure part the contents of the compartments cannot mix. The container may be provided with an upstand, preferably spaced from the side walls thereof, and preferably of
15 generally cylindrical shape. If wished, the remaining volume of the container can be divided into two or more parts by means of walls extending between the upstand and the side walls.

20 The container may be formed with an opening, for example a depression, formed in the side wall or the base wall, and preferably being open in the outward direction. That is to say, it preferably does not form part of the main volume defined by the container. Preferably the
25 opening is adapted to receive, in a press-fit manner, a solid block (for example a tablet) of a composition, for example a material useful in a washing process.

30 Preferably, the closure part is of a transparent or translucent material, so that the contents of the washing capsule can be seen.

Preferably, the container is of a transparent or translucent material, so that the contents of the washing capsule can be seen.

5 The washing composition within the container, or within a compartment thereof, need not be uniform. For example during manufacture it could be fed first with a settable agent, for example a gel, useful in a washing process, and then with a different material. The first
10 material could dissolve slowly in the washing process so as to deliver its charge over a long period within the washing process. This might be useful, for example, to provide immediate, delayed or sustained delivery of a softening agent in a clothes washing container.

15

 The container may, for example, be in at least two parts (a body part and a cap part) which fit tightly, and preferably sealingly and inseparably, together to form a compartment in which is stored the ingredient to be
20 achieved. In one example, the container or capsule may have three parts - a body such as a receptacle part, a first cap, and then a second cap to fit over the closed end of either the body or the first cap, so as to result in a capsule with two separate compartments. Where there
25 are three such parts (or more; four parts - a body and three caps - make three compartments, and so on), then naturally the ingredients in each compartment may be the same or they may be different.

30 In all embodiments of the present invention one compartment may contain, for example, a liquid or solid component (such as a powder, granules or a compressed or

gelled tablet) and another may contain a different liquid or solid component (such as a powder, granules or a compressed or gelled tablet). Alternatively, more than one component may be present in one or more compartments.

- 5 For example a compartment may contain a solid component, for example in the form of a ball or pill (such as a powder, granules or a compressed or gelled tablet), and a liquid component.

- 10 Desirably the composition has a mass of at least 10g or 15g, for example, from 10g or 15g to 100g, especially from 10g to 15g to 40g. For example, a dishwashing composition may weigh from 10g or 15g to 20g, a water-softening composition may weigh from 25g to 35g, and a
15 laundry composition may weigh from 10g to 40g, 20g to 40g or 30g to 40g.

- In general the maximum dimension of the container is 5cm. For example, a cuboid container may have a length
20 of 1 to 5cm, especially 3.5 to 4.5cm, a width of 1.5 to 3.5cm, especially 2 to 3cm, and a height of 1 to 2cm, especially 1.25 to 1.75cm.

- The composition may comprise a powder, gel, paste or
25 low water liquid foundation.

- The composition contained by the container may be, for example, any which is suitable for the designated application, for example a clothes washing or dishwashing
30 application. It may be a powder or a liquid but if a liquid, may be a low water formulation, preferably having a maximum water content of 5wt%, in order to maintain the

integrity of the walls of the capsule or a higher water formulation containing, for example, at least 8wt% water. It will be appreciated that higher water contents may be present where the water is chemically or physically bound. The composition may be formulated having regard to the fact that the user will not come into contact with the composition, whether by inhalation or by skin contact. For example, the composition may include an enzyme, without concern about physical contact between the composition containing the enzyme, and the user.


If the container contains an aqueous liquid having a relatively high free water content, it may be necessary to take steps to ensure the liquid does not attack the water-soluble polymer if it is soluble in cold water (20°C), or water at a temperature of up to, say, 35°C. Steps may be taken to treat the inside surfaces of the container, for example by coating it with agents such as PVC (poly (vinylidene chloride)) or PTFE (polytetrafluoroethylene), or to adapt the composition to ensure that it does not dissolve the polymer. For example, it has been found that ensuring the composition has a high ionic strength or contains an agent which minimises water loss through the walls of the container will prevent the composition from dissolving the polymer from the inside. This is described in more detail in EP-A-518,689 and WO 97/27743.

The composition held within the container depends, of course, on the intended use of the composition. It may, for example, contain surface active agents such as

an anionic, non-ionic, cationic, amphoteric or zwitterionic surface active agent or mixture thereof.

5 Examples of anionic surfactants are straight-chained or branched alkyl sulfates and alkyl polyalkoxylated sulfates, also known as alkyl ether sulfates. Such surfactants may be produced by the sulfation of higher C₈-C₂₀ fatty alcohols.

10 Examples of primary alkyl sulfate surfactants are those of formula:





wherein R is a linear C₈-C₂₀ hydrocarbyl group and M is a water-solubilising cation. Preferably R is C₁₀-C₁₆ alkyl, 15 for example C₁₂-C₁₄, and M is alkali metal such as lithium, sodium or potassium.

20 Examples of secondary alkyl sulfate surfactants are those which have the sulfate moiety on a "backbone" of the molecule, for example those of formula:




wherein m and n are independently 2 or more, the sum of m+n typically being 6 to 20, for example 9 to 15, and M is a water-solubilising cation such as lithium, sodium or 25 potassium.

Especially preferred secondary alkyl sulfates are the (2,3) alkyl sulfate surfactants of formulae:



for the 2-sulfate and 3-sulfate, respectively. In these formulae x is at least 4, for example 6 to 20, preferably 10 to 16. M is cation, such as an alkali metal, for example lithium, sodium or potassium.

Examples of alkoxyated alkyl sulfates are ethoxyated alkyl sulfates of the formula:



wherein R is a C_8 - C_{20} alkyl group, preferably C_{10} - C_{18} such as a C_{12} - C_{16} , n is at least 1, for example from 1 to 20, preferably 1 to 15, especially 1 to 6, and M is a salt-forming cation such as lithium, sodium, potassium, ammonium, alkylammonium or alkanolammonium. These compounds can provide especially desirable fabric cleaning performance benefits when used in combination with alkyl sulfates.

20

The alkyl sulfates and alkyl ether sulfates will generally be used in the form of mixtures comprising varying alkyl chain lengths and, if present, varying degrees of alkoxylation.

25

Other anionic surfactants which may be employed are salts of fatty acids, for example C_8 - C_{18} fatty acids, especially the sodium or potassium salts, and alkyl, for example C_8 - C_{18} , benzene sulfonates.

30

Examples of nonionic surfactants are fatty acid alkoxyates, such as fatty acid ethoxyates, especially those of formula:



wherein R is a straight or branched C_8-C_{16} alkyl group, preferably a C_9-C_{15} , for example $C_{10}-C_{14}$, alkyl group and n is at least 1, for example from 1 to 16, preferably 2 to 10
10 12, more preferably 3 to 10.

The alkoxyated fatty alcohol nonionic surfactant will frequently have a hydrophilic-lipophilic balance (HLB) which ranges from 3 to 17, more preferably from 6
15 to 15, most preferably from 10 to 15.

Examples of fatty alcohol ethoxyates are those made from alcohols of 12 to 15 carbon atoms and which contain about 7 moles of ethylene oxide. Such materials are
20 commercially marketed under the trademarks Neodol 25-7 and Neodol 23-6.5 by Shell Chemical Company. Other useful Neodols include Neodol 1-5, an ethoxyated fatty alcohol averaging 11 carbon atoms in its alkyl chain with about 5 moles of ethylene oxide; Neodol 23-9, an
25 ethoxyated primary $C_{12}-C_{13}$ alcohol having about 9 moles of ethylene oxide; and Neodol 91-10, an ethoxyated C_9-C_{11} primary alcohol having about 10 moles of ethylene oxide.

Alcohol ethoxyates of this type have also been
30 marketed by Shell Chemical Company under the Dobanol trademark. Dobanol 91-5 is an ethoxyated C_9-C_{11} fatty alcohol with an average of 5 moles ethylene oxide and

Dobanol 25-7 is an ethoxylated C_{12} - C_{15} fatty alcohol with an average of 7 moles of ethylene oxide per mole of fatty alcohol.

5 Other examples of suitable ethoxylated alcohol nonionic surfactants include Tergitol 15-S-7 and Tergitol 15-S-9, both of which are linear secondary alcohol ethoxylates available from Union Carbide Corporation. Tergitol 15-S-7 is a mixed ethoxylated product of a C_{11} -
10 C_{15} linear secondary alkanol with 7 moles of ethylene oxide and Tergitol 15-S-9 is the same but with 9 moles of ethylene oxide.

Other suitable alcohol ethoxylated nonionic
15 surfactants are Neodol 45-11, which is a similar ethylene oxide condensation products of a fatty alcohol having 14-15 carbon atoms and the number of ethylene oxide groups per mole being about 11. Such products are also available from Shell Chemical Company.

20 Further nonionic surfactants are, for example, C_{10} - C_{18} alkyl polyglycosides, such as C_{12} - C_{16} alkyl polyglycosides, especially the polyglucosides. These are especially useful when high foaming compositions are
25 desired. Further surfactants are polyhydroxy fatty acid amides, such as C_{10} - C_{18} N-(3-methoxypropyl) glycamides and ethylene oxide-propylene oxide block polymers of the Pluronic type.

30 Examples of cationic surfactants are those of the quaternary ammonium type.

The total content of surfactants in the composition is desirably 60 to 95wt%, especially 75 to 90wt%. Desirably an anionic surfactant is present in an amount of 50 to 75wt%, the nonionic surfactant is present in an amount of 5 to 50wt%, and/or the cationic surfactant is present in an amount of from 0 to 20wt%. The amounts are based on the total solids content of the composition, i.e. excluding any solvent which may be present.

10 The compositions, particularly when used as laundry washing or dishwashing compositions, may also independently comprise enzymes, such as protease, lipase, amylase, cellulase and peroxidase enzymes. Such enzymes are commercially available and sold, for example, under
15 the registered trade marks Esperase, Alcalase and Savinase by Novozymes. Desirably the enzymes are independently present in the compositions in an amount of from 0.5 to 3wt%, especially 1 to 2wt%, when added as commercial preparations they are not pure and this
20 represents an equivalent amount of 0.005 to 0.5wt% of pure enzyme.

 The compositions may, if desired, independently comprise a thickening agent or gelling agent. Suitable
25 thickeners are polyacrylate polymers such as those sold under the trade mark CARBOPOL, or the trade mark ACUSOL by Rohm and Haas Company. Other suitable thickeners are xanthan gums. The thickener, if present, is generally present in an amount of from 0.2 to 4wt%, especially 0.5
30 to 2wt%.

Compositions used in laundry washing / dishwashing independently usually comprise a detergency builder. The builders counteract the effects of calcium, or other ion, water hardness. Examples of such materials are citrate, succinate, malonate, carboxymethyl succinate, carboxylate, polycarboxylate and polyacetyl carboxylate salts, for example with alkali metal or alkaline earth metal cations, or the corresponding free acids. Specific examples are sodium, potassium and lithium salts of oxydisuccinic acid, mellitic acid, benzene polycarboxylic acids, C₁₀-C₂₂ fatty acids and citric acid. Other examples are organic phosphonate type sequestering agents such as those sold by Monsanto under the trade mark Dequest and alkylhydroxy phosphonates. Citrate salts and C₁₂-C₁₈ fatty acid soaps are preferred. Further builders are; phosphates such as sodium, potassium or ammonium salts of mono-, di- or tri-poly or oligo-phosphates; zeolites; silicates, amorphous or structured, such as sodium, potassium or ammonium salts.

20

Other suitable builders are polymers and copolymers known to have builder properties. For example, such materials include appropriate polyacrylic acid, polymaleic acid, and polyacrylic/polymaleic and copolymers and their salts, such as those sold by BASF under the trade mark Sokalan.

The builder is desirably present in an amount of up to 90wt%, preferably 15 to 90wt%, more preferable 15 to 75wt%, relative to the total weight of the composition. Further details of suitable components are given in, for example, EP-A-694,059, EP-A-518,720 and WO 99/06522.

30

The compositions can also optionally comprise one or more additional ingredients. These include conventional detergent composition components such as further
5 surfactants, bleaches, bleach enhancing agents, builders, suds boosters or suds suppressors, anti-tarnish and anti-corrosion agents, organic solvents, co-solvents, phase stabilisers, emulsifying agents, preservatives, soil
10 suspending agents, soil release agents, germicides, pH adjusting agents or buffers, non-builder alkalinity sources, chelating agents, clays such as smectite clays, enzyme stabilizers, anti-limescale agents, colourants, dyes, hydrotropes, dye transfer inhibiting agents, brighteners, and perfumes. If used, such optional
15 ingredients will generally constitute no more than 10wt%, for example from 1 to 6wt%, the total weight of the compositions.

Compositions which comprise an enzyme may optionally
20 contain materials which maintain the stability of the enzyme. Such enzyme stabilizers include, for example, polyols such as propylene glycol, boric acid and borax. Combinations of these enzyme stabilizers may also be employed. If utilised, the enzyme stabilizers generally
25 constitute from 0.1 to 1wt% of the compositions.

The compositions may optionally comprise materials which serve as phase stabilizers and/or co-solvents. Examples are C₁-C₃ alcohols such as methanol, ethanol and
30 propanol. C₁-C₃ alkanolamines such as mono-, di- and triethanolamines can also be used, by themselves or in combination with the alcohols. The phase stabilizers

and/or co-solvents can, for example, constitute 0 to 1wt%, preferably 0.1 to 0.5wt%, of the composition.

The compositions may optionally comprise components
5 which adjust or maintain the pH of the compositions at optimum levels. The pH may be from, for example, 1 to 13, such as 8 to 11 depending on the nature of the composition. For example a dishwashing composition desirably has a pH of 8 to 11, a laundry composition
10 desirable has a pH of 7 to 9, and a water-softening composition desirably has a pH of 7 to 9. Examples of pH adjusting agents are NaOH and citric acid.

The above examples may be used for dish or fabric
15 washing. In particular dish washing formulations are preferred which are adapted to be used in automatic dish washing machines. Due to their specific requirements specialised formulation is required and these are illustrated below

20

Amounts of the ingredients can vary within wide ranges, however preferred automatic dishwashing detergent compositions herein (which typically have a 1% aqueous solution pH of above 8, more preferably from 9.5 to 12,
25 most preferably from 9.5 to 10.5) are those wherein there is present: from 5% to 90%, preferably from 5% to 75%, of builder; from 0.1% to 40%, preferably from 0.5% to 30%, of bleaching agent; from 0.1% to 15%, preferably from 0.2% to 10%, of the surfactant system; from 0.0001% to
30 1%, preferably from 0.001% to 0.05%, of a metal-containing bleach catalyst; and from 0.1% to 40%, preferably from 0.1% to 20% of a water-soluble silicate.

Such fully-formulated embodiments typically further comprise from 0.1% to 15% of a polymeric dispersant, from 0.01% to 10% of a chelant, and from 0.00001% to 10% of a deterative enzyme, though further additional or adjunct ingredients may be present. Detergent compositions herein in granular form typically limit water content, for example to less than 7% free water, for better storage stability.

Non-ionic surfactants useful in ADW (Automatic Dish Washing) compositions of the present invention desirably include surfactant(s) at levels of from 2% to 60% of the composition. In general, bleach-stable surfactants are preferred. Non-ionic surfactants generally are well known, being described in more detail in Kirk Othmer's Encyclopedia of Chemical Technology, 3rd Ed., Vol. 22, pp. 360-379, "Surfactants and Deterative Systems", incorporated by reference herein.

Preferably the ADW composition comprises at least one non-ionic surfactant. One class of non-ionics are ethoxylated non-ionic surfactants prepared by the reaction of a monohydroxy alkanol or alkylphenol with 6 to 20 carbon atoms with preferably at least 12 moles particularly preferred at least 16 moles, and still more preferred at least 20 moles of ethylene oxide per mole of alcohol or alkylphenol.


Particularly preferred non-ionic surfactants are the non-ionic from a linear chain fatty alcohol with 16-20 carbon atoms and at least 12 moles particularly preferred

at least 16 and still more preferred at least 20 moles of ethylene oxide per mole of alcohol.

According to one preferred embodiment the non-ionic surfactant additionally comprise propylene oxide units in the molecule. Preferably this PO units constitute up to 25% by weight, preferably up to 20% by weight and still more preferably up to 15% by weight of the overall molecular weight of the non-ionic surfactant. Particularly preferred surfactants are ethoxylated mono-hydroxy alkanols or alkylphenols, which additionally comprises polyoxyethylene-polyoxypropylene block copolymer units. The alcohol or alkylphenol portion of such surfactants constitutes more than 30%, preferably more than 50%, more preferably more than 70% by weight of the overall molecular weight of the non-ionic surfactant.

Another class of non-ionic surfactants includes reverse block copolymers of polyoxyethylene and polyoxypropylene and block copolymers of polyoxyethylene and polyoxypropylene initiated with trimethylolpropane.


Another preferred non-ionic surfactant can be described by the formula:



wherein R^1 represents a linear or branched chain aliphatic hydrocarbon group with 4-18 carbon atoms or mixtures thereof, R^2 represents a linear or branched chain aliphatic hydrocarbon rest with 2-26 carbon atoms

or mixtures thereof, x is a value between 0.5 and 1.5 and y is a value of at least 15.

Another group of preferred nonionic surfactants are the end-capped polyoxyalkylated non-ionics of formula:




wherein R^1 and R^2 represent linear or branched chain, saturated or unsaturated, aliphatic or aromatic hydrocarbon groups with 1-30 carbon atoms, R^3 represents a hydrogen atom or a methyl, ethyl, n-propyl, iso-propyl, n-butyl, 2-butyl or 2-methyl-2-butyl group, x is a value between 1 and 30 and, k and j are values between 1 and 12, preferably between 1 and 5. When the value of x is ≥ 2 each R^3 in the formula above can be different. R^1 and R^2 are preferably linear or branched chain, saturated or unsaturated, aliphatic or aromatic hydrocarbon groups with 6-22 carbon atoms, where group with 8 to 18 carbon atoms are particularly preferred. For the group R^3 H, methyl or ethyl are particularly preferred. Particularly preferred values for x are comprised between 1 and 20, preferably between 6 and 15.

As described above, in case $x \geq 2$, each R^3 in the formula can be different. For instance, when $x=3$, the group R^3 could be chosen to build ethylene oxide ($R^3=H$) or propylene oxide ($R^3=\text{methyl}$) units which can be used in every single order for instance (PO)(EO)(EO), (EO)(PO)(EO), (EO)(EO)(PO), (EO)(EO)(EO), (PO)(EO)(PO), (PO)(PO)(EO) and (PO)(PO)(PO). The value 3 for x is only an example and bigger values can be chosen whereby a

higher number of variations of (EO) or (PO) units would arise.

Particularly preferred end-capped polyoxyalkylated
5 alcohols of the above formula are those where $k=1$ and $j=1$
originating molecules of simplified formula:



10 The use of mixtures of different non-ionic
surfactants is particularly preferred in ADW formulations
for example mixtures of alkoxyated alcohols and hydroxy
group containing alkoxyated alcohols.

15 The composition, such as a washing composition
within the container, capsule or receptacle part, or
within a compartment thereof if there is more than one
compartment, need not be uniform. For example during
manufacture it could be fed first with a settable agent,
20 for example a gel, useful in a washing process, and then
with a different material. The first material could
dissolve slowly in the washing process so as to deliver
its charge over a long period within the washing process.
This might be useful, for example, to provide delayed or
25 sustained delivery of a softening agent in a clothes
washing capsule.

The invention will now further explained with
reference to the following non-limiting Figures and
30 Examples.

BRIEF DESCRIPTION OF THE SEVERAL VIEWS OF THE DRAWINGS

The foregoing summary, as well as the following detailed description of preferred embodiments of the invention, will be better understood when read in conjunction with the appended drawings. For the purpose of illustrating the invention, there are shown in the drawings embodiments which are presently preferred. It should be understood, however, that the invention is not limited to the precise arrangements shown. In the drawings:

FIG. 1 is a view from below, of a receptacle part;

FIG. 2 is a perspective view, generally from above, of the receptacle part of Fig. 1;

FIG. 3a and FIG 3b are side views along the longitudinal and equatorial axes of the receptacle part as shown in FIG.1 and FIG. 2.

FIGS. 1 to 3 show a receptacle part 2. The receptacle part 2 has a base wall 4. The base wall 4 is substantially flat with a slight depression towards the main chamber of the receptacle part 2. The receptacle part 2 has four upright side walls 6, and has no top wall. Thus, each receptacle part 2 is upwardly open. Around its opening, at the top of the side walls 6, is an outwardly-directed flange 8, which extends around the entire opening. The flange 8 lies in one plane. When filled a cover film (not shown) may be laid over the receptacle part 2 and heat sealed against the flange 8,

so that each receptacle part 2 has, over it, a closure part (not shown).

Within the main chamber defined by the base wall 4 and side walls 6 of each receptacle part 2, there is present a generally cylindrical upstand 10, in a central position. The cylindrical upstand 10 is open at its upper end, and its upper end is in the same plane as the flange 6.

10

Adjacent the cylindrical upstand 10 there is a wave-shaped upstand 12. The wave upstand 12 extends from the base wall 4 of the receptacle part to the side walls 6 on the longitudinal axis, up to the height of the side walls 6.

15

The cylindrical upstand 10 and the wave upstand 12 divide the main chamber of the receptacle part into three separate compartments. There is a first compartment (A) within the volume defined by the cylindrical upstand 10. There are two further compartments created by the dividing effect of the wave upstand 12; a second compartment (B) on the cylindrical upstand side 10 of the wave upstand, being above the first compartment and a third compartment (C) on the opposite side of the wave upstand 12. For clarity these three compartments are shown with the letter references (A), (B) and (C) in FIG 2. The cover film is preferably sealed against the wave upstand 12, thus dividing the receptacle into separate compartments as described above.

30

CONTAINER MANUFACTURING PROCESS

This process describes a method of manufacturing a container as illustrated in the accompanying FIGS. 1-3.

5 In the filling stage it is filled with the compositions as set out in the Composition Examples.

The Moulding Stage

10 Containers according to the invention were made by the injection moulding method. The injection cavities were in a two-impression (cap/body) composite water-cooled stainless-steel mould. The PVOH had a material melt flow index of 10-20 grams/10 min (DIN 53735).
15 Injection temperatures were 175°C, 180°C, 180°C and 185°C in the feed, zone 2 and 3, and Nozzle areas. The first stage injection pressure was 400 psi, and the hold stage pressure was 270 psi. The pressure well time was 3 seconds in the first stage and 5 seconds in the hold
20 stage. Tool temperatures were between ambient and 40°C.

The moulding pressures were just sufficient to fill the cavities on the first pressure stage and then sufficient packing pressure to hold on the second stage.
25 Mould open and close rates were as fast as possible.

The moulds were such that an array of container receptacle parts were moulded simultaneously. In this case up to 64 receptacle parts could be moulded in an
30 array. Where an array was formed separation of the receptacle parts was necessary (see later).

Usually each receptacle weighed 2.0 to 2.5g. The resin used for moulding comprised 85% PVOH, 11% Sorbitol and 4% processing aids.

5 The Filling Stage

In the preferred embodiment of the invention where the container is a multi-chamber product as illustrated in the accompanying FIGS. a distinct detergent composition was added to each of the compartments. This allowed the formation of a multi-function detergent container which could be used to achieve each of the required functions in, for example, an automatic dishwasher. Indeed the following example is in the field of automatic dishwashing.

For compartment (A) generally a solidified melt formulation was added. This formulation typically comprised a surfactant which could be liquefied at elevated temperature, such as 60°C, (see Composition Examples). This formulation was added at elevated temperature in the molten state using a hot-melt nozzle dispensing device. After addition of the rinse aid the receptacle parts were placed in a cooling system to allow the rinse aid to solidify. The amount of this formulation added was usually 0.4 g.

For compartment (B) generally a powder formulation was added. This formulation was added using a powder nozzle dispensing device. For this stage of addition, vibration of the receptacle part to aid settling of the powder was employed. Also a compression station was used

to aid levelling. The amount of this formulation added was usually 0.4 g.

For compartment (C) generally a gel formulation was added. This formulation typically comprised a plurality of materials suspended in a thickened gel formulation. The formulation could be liquefied at elevated temperature, such as 60°C, (see Composition Examples). This formulation was added at elevated temperature in the molten state using a hot-melt nozzle dispensing device. The amount of this formulation added was usually 6.4 g.

The Sealing Stage

The filled receptacle parts were passed by a wetting station, comprising a "wet plate" made of sand blasted aluminium.

A sealing top film (PVOH, 80-100µm) was then applied to the wet receptacle parts.

The film was pressed onto the receptacle parts using a flat sealing surface which has been modified to follow the seal contour along the flange of the receptacle part and the wave upstand. The sealing surface operated at 150°C and pressed for 1.5 seconds.

The Separation Stage

A laser or other IR source was arranged to focus on the area of the join between individual receptacle parts in the array. The laser was applied to cut the joins

thus freeing up the individual containers.

Further Steps

5 Once sealed the containers have to be perforated on
the powder compartment top film to allow vapours to
exhaust (e.g. those vapours arising from decomposition of
the bleach components of the powder (where present)
during storage). This was done with a plate with
10 needles.

The containers were then removed from the trays to
be packed.

COMPOSITION EXAMPLES

Composition Example 1: Phosphorus Containing Composition

Raw Material	COMPARTMENT A Rinse Aid (0.4 g)	COMPARTMENT B Powder (10.4g)	COMPARTMENT C Gel (6.4 g)
Sodium tripolyphosphate		43	
Sodium carbonate		16	
Sodium percarbonate		22	
Phosphate speckles		4	
Benzotriazol		0.4	
HEDP 4 Na (88,5%)		0.3	
Protease ¹		1.5	
Amylase ¹		1	
TAED		6	
1,2-Propylenediglycol		1	
Dye		0.02	
Perfume		0.1	
Sulphonated Polymer ²		5	
Sulphonated Polymer ²			5
Surfactant ³			24
Polyglykol ⁴			9
1,2-Propylendiglycol			1
Dye			0.03
Antifoam ⁵			0.25
TAED			3
Sodium tripolyphoshate			57.5
Polyglycol 6000			0.3
Surfactant ⁶	100		
	100	100	100

5

1 Granules which contain approx. 10% active enzyme.

2 AMPS co-polymer.

3 Non-ionic low foaming surfactant.

4 Mixed poly alkoxylate.

10

5 Silicone oil.

6 Non-ionic surfactant (m.pt. approx. 50°C)

The receptacle part weighed 2.5g and comprised 85% of low molecular weight PVOH (degree of hydrolysis 85-

88%), 11% sorbitol and 4% processing aids. The receptacle lid comprised a PVOH foil (90µm thick).

5 The contents of Compartment A (the non-ionic surfactant (6)) were heated at 55°C until molten. The contents were added into Compartment A and chilled to solid. The powder was filled into Compartment B. The gel was heated to 65°C and stirred for 20 minutes. The gel was filled into Compartment C and allowed to chill.

10

The receptacles were then sealed with PVOH film.

Composition Example 2: Phosphorus-Reduced Composition

Raw Material	COMPARTMENT A Rinse Aid (0.4 g)	COMPARTMENT B Powder (10.4g)	COMPARTMENT C Gel (6.4 g)
Sodium Citrate		26	
Sodium tripolyphosphate		19	
Sodium carbonate		16	
Sodium percarbonate		22	
Phosphate speckles		4	
Benzotriazol		0.4	
HEDP 4 Na (88,5%)		0.35	
Protease ¹		1.5	
Amylase ¹		1	
TAED		6	
1,2-Propylenediglycol		1	
Dye		0.02	
Perfume		0.1	
Sulphonated Polymer ²		5	
Sulphonated Polymer ²			5
Surfactant ³			24
Polyglykol ⁴			9
1,2-Propylendiglycol			1
Dye			0.03
Antifoam ⁵			0.25
TAED			3
Sodium tripolyphosphate			57.5
Polyglycol 6000			0.3
Surfactant ⁶	100		
	100	100	100

1 Granules which contain approx. 10% active enzyme.

5 2 AMPS co-polymer.

3 Non-ionic low foaming surfactant.

4 Mixed poly alkoxylate.

5 Silicone oil.

6 Non-ionic surfactant (m.pt. approx. 50°C)

10

The preparation was as for Example 1.

Composition Example 3: Phosphorus Free Composition

Raw Material	COMPARTMENT A Rinse Aid (0.4 g)	COMPARTMENT B Powder (10.4g)	COMPARTMENT C Gel (6.4 g)
Tri-sodium citrate		51.5	
Sodium carbonate		15	
Sodium percarbonate		20	
Benzotriazol		0.4	
HEDP 4 Na (88,5%)		0.3	
Protease ¹		1.5	
Amylase ¹		1	
1,2-Propylenediglycol		1	
Dye		0.02	
Perfume		0.1	
Acrylate homo polymer		3	
Sulphonated Polymer ²			5
Surfactant ³			24
Polyglykol ⁴			9
1,2-Propylendiglycol			1
Dye			0.03
Antifoam ⁵			0.25
TAED			8
Tri-sodium citrate			51.75
Polyglycol 35000			1
Surfactant ⁶	100		
	100	100	100

1 Granules which contain approx. 10% active enzyme.

5 2 AMPS co-polymer.

3 Non-ionic low foaming surfactant.

4 Mixed poly alkoxyate.

5 Silicone oil.

6 Non-ionic surfactant (m.pt. approx. 50°C)

10

The preparation was as for Example 1.

Composition Example 4: Phosphorus Containing Composition with a bleach activator composition in the centred compartment

Raw Material	COMPARTMENT A Melt (1.5 g)	COMPARTMENT B Powder (9.2g)	COMPARTMENT C Gel (6.4 g)
Sodium tripolyphosphate		52	
Sodium carbonate		15	
Sodium percarbonate		20	
Phosphate speckles		4	
Benzotriazol		0.4	
HEDP 4 Na (88,5%)		0.3	
Protease ¹		1.5	
Amylase ¹		1	
1,2-Propylenediglycol		1	
Dye		0.02	
Perfume		0.1	
Sulphonated Polymer ²		5	
Sulphonated Polymer ²			5
Surfactant ³			24
Polyglykol ⁴			9
1,2-Propylendiglycol			1
Dye			0.03
Antifoam ⁵			0.25
Sodium tripolyphoshate			61
Polyglycol 6000			0.3
Gelatine	3		
Glycerine	47		
TAED	50		
	100	100	100

5

1 Granules which contain approx. 10% active enzyme.

2 AMPS co-polymer.

3 Non-ionic low foaming surfactant

4 Mixed poly alkoxyate grade.

10 5 Silicone oil

The preparation was as for Example 1.

Composition Example 5: Phosphate Containing Composition
Including PAP

Raw Material	COMPARTMENT A (1.5 g)	COMPARTMENT B Powder (9.2 g)	COMPARTMENT C Gel (6.4 g)
Sodium tripolyphosphate		42.5	
Sodium carbonate		16	
Tri-sodium citrate		22	
Phosphate speckles		4	
Benzotriazol		0.4	
HEDP 4 Na (88,5%)		0.3	
Protease ¹		1.5	
Amylase ¹		1	
TAED		6	
1,2-Propylenediglycol		1	
Dye		0.02	
Perfume		0.1	
Sulphonated Polymer ²		5	
Sulphonated Polymer ²			5
Surfactant ³			24
Polyglykol ⁴			9
1,2-Propylendiglycol			1
Dye			0.03
Antifoam ⁵			0.25
TAED			3
Sodium tripolyphosphate			57.5
Polyglycol 6000			0.3
PAP ⁶	100		
	100	100	100

5 1 Granules which contain approx. 10% active enzyme.

2 AMPS co-polymer.

3 Non-ionic low foaming surfactant.

4 Mixed poly alkoxyate grade.

5 Silicone oil

10 6 PAP granules of particle size > 250µm.

In the container used in this Example the cylindrical part is raised to the height of the side wall. The PAP is added as a powder. The remainder of the preparation process is as for Example 1.

5

Rigidity Examples

Rigidity Example 1

10

A receptacle part as illustrated in the accompanying Figures was made in an injection moulding process. The receptacle part had the overall dimensions of 40mm (length), 28mm (width) and 18mm (height). The thickness of the receptacle was 300µm with a rim thickness of 700µm.

15

The composition of the receptacle part was the same as that of the composition Examples.

20

The rigidity of the receptacle part was measured using a measuring device available from Imatec in accordance with the DIN 878 method. Using this apparatus a force of 0.8N was applied to the receptacle part (across its width) with a needle having a width of 2.4mm.

25

Measurements were taken immediately after production of the receptacle part and after storage in moist conditions (after 15 minutes and 30 minutes at 30°C and 70% humidity. The rigidity data, shown in terms of the deformation extent of the receptacle part is shown in the following table.

30

The following table also contains values for the brittleness of the receptacle part, in terms of the force required to break the container, measured using the same equipment.

5

Receptacle	Deformation (mm)			Brittleness (N)
	Minimum	Average	Maximum	
Immediately After Production	0.54	0.89	1.14	<80
15 min. at 30°C / 70% humidity	1.10	1.33	1.69	-
15 min. at 30°C / 70% humidity	1.38	1.69	2.76	>100

10 The deformation ability of the receptacle party increases significantly after plasticisation by water in the humid atmosphere. This has the beneficial effect that as the receptacle part has a low deformation ability (high rigidity) after production it can be filled and sealed effectively without any incorrect filling / poor sealing. After plasticisation the container has a high
15 deformation ability (low rigidity) which is pleasing to a consumer on a tactile level.

The container also has a much lower brittleness after plasticisation. This allows the container to be
20 transported and handled without causing rupture of the container.

CLAIMS

1. A process for the manufacture of a single or multi-compartment, rigid, water-soluble container, containing a detergent composition, wherein the container is at least partially formed of injection moulded water soluble polymer; the process comprising the steps of forming the container, filling with the detergent composition and sealing.
2. A process according to claim 1, wherein the container is allowed to contact/brought into contact with a plasticiser after sealing.
3. A process according to claim 2, wherein the plasticiser is water.
4. A process for the manufacture of a single or multi-compartment, rigid, water-soluble container, containing a detergent composition, wherein the container is at least partially formed of injection moulded water soluble polymer; the process comprising the steps of forming the container, keeping the container under substantially anhydrous conditions, filling with the detergent composition and sealing.
5. A process according to claim 4, wherein the container comprises a PVOH polymer or a derivative thereof.
6. A process according to claim 5, wherein the container comprises an additional injection moulded water-soluble polymer, which when dissolved in water is

active in detergency.

7. A process according to claim 6, wherein the additional injection moulded water-soluble polymer is
5 poly(vinylpyrrolidone), poly(acrylic acid) or an ester thereof or poly(maleic acid) or an ester thereof, or a copolymer of any thereof.

8. A process according to claim 5,6 or 7, wherein the
10 first and additional polymer(s) are simultaneously or sequentially injection moulded.

9. A process according to any one of the preceding claims wherein the container is made from a water-soluble
15 receptacle part and is sealed by a water-soluble closure part, preferably in the form of a film or injection-moulded, rigid closure.

10. A process according to claim 9 wherein the closure
20 part comprises a poly(vinyl alcohol) film or closure.

11. A process according to claim 9 or claim 10 wherein the receptacle part has side walls which terminate at their upper end in an outward flange, to which the
25 closure part is sealingly secured.

12. A process according to claim 9 wherein the closure part comprises a plastic film.

30 13. A process according to any one of the preceding claims wherein the detergent composition comprises a powder, gel, paste or low water liquid formulation.

14. A process according to any one of claims 11 to 13 wherein the container comprises a tablet formulated for delayed and/or sustained release of a material.

5

15. A process according to claim 9 wherein the receptacle part comprises an upstanding wall which separates compartments thereof.

10 16. A process according to any one of claims 9 to 15 wherein the closure part is a transparent or translucent material.

15 17. A process as claimed in any one of the claims 1 to 16, wherein the containers are joined together in an array arrangement, but are readily separable from each other for use.

20 18. A method of manufacture of an array as defined in claim 17, which method comprises: forming an array of receptacle parts, each receptacle part being connected to adjacent receptacle parts, but being separable from them by a snap or tear action; charging the receptacle parts with washing composition; and sealingly securing a sheet
25 of a water-soluble polymer over the top of the array, to form the closure parts for all the receptacle parts of the array.

30 19. A process as claimed in any claim from 1 to 16, which comprises melting the polymer(s), injecting the molten polymer(s) into a mould, removing the rigid water soluble container from the mould and adding the fabric

care, surface care, or dishwashing composition into the container.

20. A process according to claim 19 wherein a first
5 polymer and an additional polymer(s) are simultaneously
or sequentially injected into the mould.

21. A process according to claim 20 wherein the first
polymer and the additional polymer(s) are sequentially
10 injected into the mould, in any order, by one of the
following techniques, multi-component injection moulding
or sandwich injection moulding.

22. A process according to claim 21 wherein the first
15 polymer and the additional polymer(s) are sequentially
injected into the mould, in any order, injection moulding
a polymer or molten polymer mix into a mould, removing
the solid polymer and inserting into a second mould and
injection moulding a second polymer or polymer mix into
20 the second mould.

23. A process according to claim 21 wherein the first
polymer and the additional polymer(s) are sequentially
injected into the mould, in any order, injection moulding
25 a polymer or molten polymer mix into a part of a mould,
injection moulding a second polymer or molten polymer mix
into a further part of the mould.

24. A process according to claim 21 wherein the first
30 polymer and the additional polymer(s) are simultaneously
injection moulded into the mould as a molten mix.

25. A process for the manufacture of a single or multi-compartment rigid, water-soluble container, containing a detergent composition, comprising: -

- 5 (i) Forming an array of containers in an injection moulding process;
- (ii) Removing the array from the mould;
- (iii) Placing the array in a storage area, substantially free of moisture;
- 10 (iv) Filling the array of containers with the detergent composition;
- (v) Placing a closure on the array;
- (vi) Sealing the containers; and
- (vii) Separating the array into individual containers;

ABSTRACT

INJECTION MOULDED CONTAINERS

5 A process for the manufacture of single or multi-
compartment rigid, water-soluble container, containing a
detergent composition wherein the container is at least
partially made of injection moulded water soluble
polymer; the process comprising the steps of forming the
10 container, keeping the container under substantially
anhydrous conditions, filling the container with the
detergent composition and sealing.




Fig 1

1/3




Fig 2




Fig 3

PCT/GB2004/005262



**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☒ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.